

imagine. change


# Super premium

Resin . Flat head . Near edge









- Superior ironing resistance at temperature up to 150°C.
- The printed image is very resistant to water washing, dry cleaning, stone wash and bleach.
- Ricoh's unique coating on the back allows reliable and superior matching qualities with the thermal head.

Application

### PRINTING PROPERTIES

Maximum printing speed 6 IPS



	Nylon	Polyester satin	Acetate
Compatibility	Q	$ \emptyset $	Ø
Image density	1.42	1.47	1.33

Image resolution for paper & film:

Minimum size:

- For the lines: 4.0 mm

- For the characters: 1.0mm

### RIBBON PROPERTIES

Total ribbon thickness: < 9 μm</li>

• Polyester film thickness: 4.5 μm

• Friction coefficient: < 0.050

• Ink melting point: 83°C

Tearing resistance: > 200N/mm<sup>2</sup>

Transmission density: 0.65 mini

# **CERTIFICATES/ DIRECTIVES**











### **GENERAL CONDITION**

Usage conditions: 5 to 35°C at 30 to 85% of relative humidity.

Storage conditions: Keep indoor avoiding high temperature (such as beside

a heat source), high humidity, direct sunlight.

Storage life: 12 months after slitting day.



# PRINTED IMAGE DURABILITY

TESTS with standard nylon care labels	RESULTS
Standard wash	ANSI > B
25 washing at 40°C during 45 min • Test ISO C06A1M	
Standard wash	ANSI > B
25 washing at 60°C during 45 min • Test ISO C06A1M	
Stone wash	ANSI > C
1 time	
Dry cleaning	ANSI > B
5 times	
Direct & indirect ironing (150°C)	ANSI > B
20 back and forwards	
Bleaching	ANSI > B
diluted to 5% during 2h	
Light	ANSI > B
Xenon lamp at 650W/m² during 1 month	

## **D110A DURABILITY**



These performances are for guidance only. Results are obtained with adapted receiving material and optimum print conditions. (Ricoh test method)

### RICOH VIETNAM COMPANY LTD.

F17, E.Town Central, 11 Doan Van Bo, Ward 13, District 4, HCM City

Tel: +84 28-3528-5252 Fax: +84 28-3636-7211

Email: thermal@ricoh.com.vn Website: https://ricoh.com.vn/products/thermal



